



Castrol Techniclean 3659

Alkaline cleaner

Description

Castrol Techniclean™ 3659 is an oil-rejecting cleaner formulated for use on turbo and spray washers. The Techniclean 3659 product is a medium to heavy duty cleaner which provides excellent detergency while providing superior in-process corrosion protection. Designed to be silicate-free, this product will not interfere with subsequent painting operations.

Application

Techniclean 3659 effectively removes a variety of medium to heavy soils such as forming and lapping compounds, greases, and rust inhibiting waxes from ferrous parts.

It is suitable for use in a wide range of modern cleaning equipment, which includes spray and intensive flood wash as well as all types of dip and ultrasonic applications.

Conditions of Use

Spray: 3 - 10% concentration; 130° - 180° F (54° - 82° C)

Ultrasonic: 3 - 10% concentration; 130° - 180° F (54° - 82° C)

Optimum conditions of use are depending on

the detailed application requirements and the amount and nature of the soil being removed.

Ideal foam control will occur at temperatures greater than 130 °F.

Advantages

- High level of rust inhibitors provide additional in-process corrosion protection
- Silicate free to allow for superior paint adhesion in downstream processes
- Low surface tension improves surface wettability

Typical Characteristics

Name	Method	Units	Value
Appearance of Concentrate	Visual	-	Straw-coloured Fluid
pH of Concentrate	CN-TM-069	-	11.7
pH of Solution at 3%	CN-TM-069	-	11.2
Specific Gravity at 60°F (16°C)	CN-TM-086	-	1.06
Bulk Density	-	lbs/gal	8.8
Nitrates	-	-	None
Phosphates	-	-	None
Silicates	-	-	None

User Advice

Techniclean 3659 is safe to use on ferrous metals. Consult your Castrol Sales Engineer for questions regarding compatibility.

Additional Information

Concentration Control

% Concentration	Refractometer Reading
3.0	0.84
5.0	1.40
7.0	1.96
10.0	2.80

Castrol Techniclean 3659

18 Mar 2011

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

www.castrol.com/industrial