



Product Data

## Braycote™ 444

Extended Life Grease for Aircraft Airframe Equipment

### Description

Castrol Braycote™ 444 (previously called Aeroplex™ 444) is a hybrid synthetic, lithium complex NLGI Grade 2 grease. It contains proprietary Castrol additives and offers excellent low temperature properties. Braycote 444 has enhanced anti-wear, oil separation, corrosion resistance, and low temperature torque characteristics.

### Application

Braycote 444 is an extended-life grease designed for use in aircraft airframe equipment. It was specifically developed for the Boeing Company and is approved to Boeing Specification BMS 3-34. Typical uses include roller bearings, actuator screws and other airframe equipment. This product should be used in accordance with the guidelines and maintenance practices specified by Boeing in applications requiring a BMS 3-34 grease or according to the requirements of other aircraft manufacturers.

**Temperature Range** Braycote 444 will operate over the temperature range of -100°F to a maximum of 250°F (-73°C to 121°C).

**Specification** Braycote 444 is approved to BMS 3-34.

## Typical Characteristics

Name	Method	Units	Braycote 444
Unworked Penetration	ASTM D217 / IP 50	0.1 mm	298
Worked Penetration (60 strokes @ 25°C / 77°F)	ISO 2137 / ASTM D217	0.1 mm	309
Worked Penetration (100,000 strokes @ 25°C / 77°F) - change from 60 strokes	ISO 2137 / ASTM D217	0.1 mm	316
Low temperature Torque @ -73°C / -100°F - starting torque	ASTM D1478	Nm	0.45
Low temperature Torque @ -73°C / -100°F - torque after 60 mins	ASTM D1478	Nm	0.04
Low temperature Torque @ -73°C / -100°F with 15% water - starting torque	ASTM D1478	Nm	4.80
Low temperature Torque @ -73°C / -100°F with 15% water - torque after 60 mins	ASTM D1478	Nm	0.07
Four Ball Weld Load test - Weld Point	ISO 11008 / ASTM D2596	kgf	400
Four Ball Weld Load test - Load Wear Index (27°C / 1770 rpm)	ISO 11008 / ASTM D2596	-	61
Four Ball Wear test - Wear Scar Diameter (40 kgf / 75°C / 1200 rpm / 1 hr)	DIN 51350 / ASTM D2266	mm	0.47
Fretting Wear test	ASTM D4170	wt loss (mg)	1.6
High Temperature Bearing Life test	ASTM D3336	hrs	1754
Oil Separation (250 hrs @ 177°C / 350°F)	ASTM D6184 / FTM 321.2	% wt	3.50
Oxidation Stability - Rotating Pressure Vessel test @ 100 hrs	ASTM D942 / DIN 51808	pressure drop psi	4
Oxidation Stability - Rotating Pressure Vessel test @ 500 hrs	ASTM D942 / DIN 51808	pressure drop psi	9
Rust Test - EMCOR (synthetic seawater)	ISO 11007 / ASTM D6138	Rating	Pass
Copper Corrosion (24 hrs, 100°C / 212°F)	ASTM D4048	Rating	1b
Water Wash-out	ISO 11009 / ASTM D1264	% wt loss	3.7

Subject to usual manufacturing tolerances.

**This product was previously called Aeroplex 444. The name was changed in 2015.**

Braycote™ 444

12 Jan 2018

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Lubricants USA Inc., 1500 Valley Road, Wayne, NJ 07470  
Telephone: +1-888-CASTROL Product Information: +1-877-641-1600  
[www.castrol.com/en\\_us/b2b/home.html](http://www.castrol.com/en_us/b2b/home.html)