



Product Data

Rustilo™ 66 VCI

Neat corrosion preventive oil with Vapour Corrosion Inhibitor

Description

Castrol Rustilo™ 66 VCI is an oil type protective containing a vapour-phase corrosion inhibitor (VCI).

Application

Rustilo 66 VCI has been specifically designed for simultaneously cleaning and protecting ball and roller bearings. It is also suitable for the protection of all types of delicate or highly finished engineering products, particularly those, which contain moving parts and cannot be protected with greasy film coatings.

Rustilo 66 VCI can be applied by immersion in a suitably designed treatment tank, which should be covered when not in use. It can also be applied by spray.

Advantages

- Free from hydrocarbon solvents, supports compliance with EC Solvent Directive (1999/13/EC).
- Heavy metals free (for example Barium), which may help to fulfil aspects of legislative requirements and waste treatment requirements that specify that these chemicals are excluded.
- Additional rust prevention through Vapour Corrosion Inhibitor. The maximum protection is achieved in hermetically sealed packs (safe pack).
- Contains no additives which inhibit the even distribution of oil and grease (e.g. silicone)
- Very good age resistance enables long service life and ensures best cleanability even after temperature exposure.
- Compatible with most mineral oil and greases
- Shows very good filtering properties
- If required protective films of Rustilo 66 VCI can be removed by using a petroleum solvent or alkaline process cleaner, all available from Castrol.

Typical Characteristics

Description	Method	Unit	Rustilo 66 VCI
Appearance	CN-TM-007	-	Clear, amber liquid
Specific Gravity @ 15°C	CN-TM-084	g/ml	0.88 - 0.91
Viscosity, Kinematic @ 40°C	ASTM D445	cSt	10.5 - 14.5
Film Type	Visual	-	Thin, Oily
Corrosion Protection	Indoor Storage (sealed pack)	Years	Up to 5
	(*) Indoor storage	Month	12
Flash Point, PMCC	CN-TM-037	°C	160 - 165

Subject to usual manufacturing tolerances.

Additional Information

The claims on film thickness and consumption are average values. These are valid for smooth surfaces with good drain-off characteristics and simple geometries without holes or recesses.

(*) "Indoor storage" describes the storage of ferrous components in closed store-rooms having a relative humidity of 60%. Increased protection times could be achieved when treating finished surfaces or store the parts in a sealed pack.

Storage

To avoid product deterioration always keep the container/drum tightly sealed. Store the product in a cool, dry place away from direct sunlight. Prevent exposure to frost and avoid water ingress. For optimum product stability, it is preferable to store the product indoors between 5°C and 45 °C / 41°F and 113°F.

Influence of temperature may cause some cloudiness, which is reversible and does not have an impact on product quality or corrosion protection performance in most instances.

For more details, please refer to the product safety data sheet.

Rustilo™ 66 VCI

12 Jan 2018

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Lubricants USA Inc., 1500 Valley Road, Wayne, NJ 07470
Telephone: +1-888-CASTROL Product Information: +1-877-641-1600
www.castrol.com/en_us/b2b/home.html