



Product Data

Braycote Micronic 601 EF

Grease, Rust Preventive, Rocket Propellant Compatible

Description

Castrol Braycote[®] Micronic 601 EF is a smooth, buttery, translucent, off-white, NLGI #2 grease. Its base oil (Castrol Brayco[®] 815Z) is a perfluorinated polyether, with exceptional chemical resistance, extremely low volatility, and a wide temperature service range. The grease is non-toxic, nonflammable, and does not use any chlorofluorocarbons (CFC's) during product manufacture. This product exhibits unusually high load-carrying capabilities as measured by the Four-Ball EP Test, and contains a rust and corrosion inhibitor for extra component protection. Castrol Brayco[®] IC X-100 can be used to remove this lubricant. Refer to the Brayco IC X-100 data sheet for further information.

Application

Braycote Micronic 601 EF is designed to operate in the presence of rocket fuels, oxidizers and high vacuum. It is frequently used in space applications including the Space Shuttle and satellites. It should also be considered in any application where a hostile chemical or extreme environmental conditions would preclude the use of an ordinary grease. Typical applications include ball and roller bearings, gears, and as an assembly lubricant for O-rings and elastomers. Perfluorinated greases, such as, this product, exhibit excellent shelf life due to their intrinsic inertness.

Temperature Range: -80°C to 204°C (-112°F to 400°F)

Conditions of Use

Limitations:

Braycote Micronic 601 EF is compatible with most commonly utilized materials, plastics, and elastomers. It may be adversely affected by Lewis Acid Catalysts such as Aluminum Chloride, at elevated temperatures. Newly exposed rubbing surfaces of aluminum, magnesium and titanium alloys may react with this product under certain conditions. Such systems should be thoroughly evaluated. Surfaces must be well cleaned of organic rust inhibitors prior to grease application to insure proper lubrication. This product is not recommended for use in applications under high vacuum with loads exceeding 100,000 psi for extended periods of time.

Packaging

Braycote Micronic 601 EF is available in 2 oz and 4 oz (AVDP) disposable polypropylene syringes and 1 pound jars.

Typical Characteristics

Name	Method	Units	Braycote Micronic 601 EF
Unworked Penetration	ISO 2137/IP 50	0.1 mm	288
Worked Penetration (60 strokes @ 25 °C/77 °F)	ISO 2137/ASTM D217	0.1 mm	290
Oil Separation (30 hrs @ 100 °C/212 °F)	ASTM D6184	% wt	10.53
Rust Test (distilled water)	ASTM D1743	Rating	Pass
Copper Corrosion (24 hrs, 100 °C/212 °F)	ASTM D4048	Rating	1b
Dropping point	ASTM D2265	°C/°F	208/407
Four Ball Weld Load test - Weld Point	ISO 11008/ASTM D2596	kgf	800+
Vacuum Stability	ASTM E595 / NASA SP-R-0022A	Total Weight Loss (% wt) / Volatiles (%wt)	0.39/0.03
Low temperature Torque - starting torque @ -62 °C/-80 °F	ASTM D1478	Nm	0.06
Low temperature Torque - torque after 60 mins @ -62 °C/-80 °F	ASTM D1478	Nm	0.02
Low temperature Torque - starting torque @ -73 °C/-100 °F	ASTM D1478	Nm	0.140
Low temperature Torque - torque after 60 mins @ -73 °C/-100 °F	ASTM D1478	Nm	0.06
LOX Impact Sensitivity (100mm, 20 drops)	-	Pass	Pass
Evaporation Loss(22hrs @ 204 °C/400 °F)	ASTM D2595	% wt	0.87
Density of finished grease @ 15 °C/59 °F	In-house test	lb/gallon	16.17
Density of finished grease @ 15 °C/59 °F	In-house test	g/ml	1.94
Specific Gravity @ 15 °C/59 °F	ASTM D287	-	1.8531
Base Oil Density @ 15 °C/59 °F	ASTM D4052/DIN 51757D	kg/m³	1848.9
Base Oil Viscosity @ 99 °C/210 °F	ISO 3104/ASTM D445	mm²/s	45
Base Oil Viscosity @ 38 °C/100 °F	ISO 3104/ASTM D445	mm²/s	148
Base Oil Viscosity @ -54 °C/-65 °F	ISO 3104/ASTM D445	mm²/s	10,855
Viscosity Index	ISO 2909/ASTM D2270	-	350
Pour Point	ISO 3016/ASTM D97	°C/°F	-72/-100
Knudsen Vapour Pressure @ 20 °C	-	Pa	0.000000000532
Knudsen Vapour Pressure @ 100 °C	-	Pa	0.00000266
Knudsen Vapour Pressure @ 200 °C	-	Pa	0.000266

Braycote Micronic 601 EF

26 Aug 2020

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Lubricants USA Inc., 1500 Valley Road, Wayne, NJ 07470
 Telephone: +1-888-CASTROL Product Information: +1-877-641-1600
www.castrol.com/en_us/b2b/home.html