CLARION® Food Machinery HT EP Greases



OVERVIEW



• High temperature, extreme pressure (EP), water resistant greases in NLGI No. 1 and 2 grades.

FEATURES & BENEFITS



- Superior extreme pressure (EP) and antiwear performance.
- Excellent rust protection.
- High dropping point and oxidation inhibited for high temperature use.
- Excellent adhesion for sealing and water washout resistance.
- Excellent pumpability (NLGI No.1).
- NSF H1 registered for use in food processing plants under the jurisdiction of the USDA.
- Certified under NSF/ANSI/CAN Standard 61 (NLGI No. 2 only)



APPLICATIONS



- For use with food processing and packaging machinery where there is a possibility of incidental contact with food.
- NLGI No. 1 grade is ideal for use in centralized lubrication systems such as those used with beverage bottle fillers.

PROPERTIES



Typical Properties for CLARION Food Machinery HT EP Greases:

NLGI No.	1	2
Material Code	655701009	655700009
Thickener Type	Aluminum Complex	Aluminum Complex
Texture	Smooth, Tacky	Smooth, Tacky
Color, Observed	White to Off-White	White to Off-White
Worked Penetration, ASTM D217	310-340	265-295
Dropping Point, ASTM D566, °F (°C)	450 (232)	500 (260)
Wheel Bearing Leakage, ASTM D1263, % loss	N/A	4.5
Water Washout, ASTM D1264, % loss	N/A	7.7 @ 175°F
Water Spray Resistance, ASTM D4049, % loss	N/A	9.2
Rust Prevention, ASTM D1743, rating	Pass	Pass
Copper Corrosion, ASTM D4048, rating	1a	1a
Oil Separation, ASTM D1742, % loss	2.0	2.0
Timken Test, ASTM D2509, OK load, lbs	40	40
Four-Ball Wear, ASTM D2266, mm	0.55	0.55
Four-Ball EP Weld, ASTM D2596, kgf	400	400
Four-Ball Load Wear Index, ASTM D2596, kgf	55	55
Approximate Temperature Range, °F (°C)	-5 to 350 (-21 to 177)	10 to 350 (-12 to 177)
NSF Registered (Registration Number)	H1 (142230)	H1 (124605)
NSF/ANSI/CAN Standard 61 Certified	-	✓
FDA, 21 CFR 178.3570	v	~

Characteristics of Oil Plus Oil Soluble Additives:

Viscosity ASTM D445		
cSt @ 40°C	581	581
cSt @ 100°C	65.8	65.8
Viscosity Index ASTM D2270	188	188

CLARION is a registered trademark of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners. Values shown are typical values only and do not constitute a specification. The information contained herein is subject to change without notice.