

# CERAN XM 460



Grease



Extreme-pressure water resistant high temperature **"NEW GENERATION"** calcium sulfonate complex grease

## APPLICATIONS

Multi purpose heavy duty water resistant grease. Shock loaded applications in industry even in severe demanding environment (water, dust, high temperature).

- **CERAN XM 460** is made of the **NEW GENERATION** calcium sulfonate complex soap designed by TOTAL Lubrifiants. This new soap has enhanced properties in terms of water and thermal resistance, load capacity, anticorrosion properties while keeping a very high level of pumpability and ability to lubricate well in case of high loads.
- **CERAN XM 460** is suitable for the lubrication of all kinds of components subject to high loads and temperatures, shocks, working in conditions where the grease is in frequent contact with water (even sea water due to enhanced antirust performances).
- **CERAN XM 460** is suitable for the lubrication of **bearings in steel plants** (continuous castings and rolling mills) and in **paper industry**. **Ceran XM 460** is also suitable for the lubrication of hard wood **granular presses** and in all industrial applications under severe conditions (wet, loaded, high temperature, dust,...) namely **mining and cement industries**.
- **CERAN XM 460** is suitable for use in centralized greasing systems.
- Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system.

## SPECIFICATIONS

- ISO 6743-9: L-XBFB 1/2
- DIN 51 502: KP1/2R -25

## ADVANTAGES

True multi purpose. Shock loads. Water resistant. Anti corrosion.

**NEW GENERATION** allowing use in high speed factors.

No harmful substances.

- The **NEW GENERATION** of calcium sulfonate complex soap developed by TOTAL Lubrifiants allows **CERAN XM 460** to present outstanding performances even at high nDm. This **NEW GENERATION** keeps all benefits in terms of corrosion protection, bearings lifetime, high loads and thermal resistance.
- Excellent anti-oxidation and anti-corrosion properties thanks to the excellent behaviour of the calcium sulfonates, also in the presence of sea water.
- The **NEW GENERATION** of calcium sulfonate complex soap allows to keep outstanding **CERAN XM 460** performances even in case of high speed applications where normally polyurea or lithium complex greases are requested.
- **CERAN XM 460** does not contain lead, or other heavy metals considered harmful to human health and the environment.

**TOTAL Specialties USA, Inc.**

Linden, NJ 07036  
5 North Stiles Street  
1-800-323-3198  
www.totalspecialties.com

CERAN 7-2016

This lubricant must be applied as recommended and used for the application for which it was designed. TOTAL Specialties USA, Inc. will have no responsibility for any injury to persons or property resulting from misuse or misapplication of the lubricant. A safety data sheet conforming to the OSHA Hazard Communication Standard 29 CFR Section 1910.1200 can be downloaded at [www.totalspecialties.com](http://www.totalspecialties.com). Copyright 2016 All rights reserved.



TYPICAL CHARACTERISTICS	METHODS	UNITS	CERAN XM 460 (typical values)
Soap/thickener		-	Calcium sulfonate complex
NLGI grade	ASTM D 217/DIN 51 818	-	1-2
Color	Visual	-	Brown
Appearance	Visual	-	Smooth
Operating temperature range		°C	- 25 to 180
Kinematic viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/ IP71	mm <sup>2</sup> /s (cSt)	460
<b>Mechanical stability</b>			
Penetration at 25°C	ASTM D 217/DIN 51 818	0.1 mm	280-310
Penetration after 100 000 strokes	ISO 2137	0.1 mm	+21
Shell Roller 100 hours at 80°C	ASTM D 1831 mod	0.1 mm	0
Shell Roller 100 hours at 80°C + 10% water	ASTM D 1831 mod	0.1 mm	-34
<b>Thermal stability</b>			
Dropping point	IP 396	°C	> 300
Oil release 50 hours, 100 °C Oil	ASTM D 6184	%	1.7
release 168 hours, 40°C Oxidation stability at 99°C +-0.5°C	NF T 60-191	%	1.1
Pressure drop after 100 hours	ASTM D 942	Psi	5
Pressure drop after 500 hours		Psi	16
<b>Antirust properties</b>			
EMCOR, distilled water	ISO 11007	Rating	0-0
EMCOR, synthetic sea water	ISO 11007	Rating	0-0
Copper corrosion, 24 hours at 100°C	ASTM D 4048	Rating	1b
<b>Antiwear and EP properties</b>			
Four ball wear (scar diameter)	ASTM D2266	mm	0.43
Four ball weld load	ASTM D2596	kgf	500
<b>Cold properties</b>			
Penetration at -20°C	ISO 13737	0.1 mm	95
Flow pressure at -20°C	DIN 51 805	mbar	1160
Flow pressure at 1400 mbar	DIN 51 805	°C	-25
Torque at -20°C			
Starting torque	ASTM D 1478	g.cm	890
After 1 hour		g.cm	72

Above characteristics are mean values given as an information.

## TOTAL Specialties USA, Inc.

Linden, NJ 07036

5 North Stiles Street

1-800-323-3198

www.totalspecialties.com

CERAN 7-2016

This lubricant must be applied as recommended and used for the application for which it was designed. TOTAL Specialties USA, Inc. will have no responsibility for any injury to persons or property resulting from misuse or misapplication of the lubricant. A safety data sheet conforming to the OSHA Hazard Communication Standard 29 CFR Section 1910.1200 can be downloaded at [www.totalspecialties.com](http://www.totalspecialties.com). Copyright 2016 All rights reserved.