

CITGO CITGARD® 600 MULTI-VISCOSITY  
GRADE ENGINE OILS



Date 08/11

**DESCRIPTION:** CITGO CITGARD 600 Multi-Viscosity Grade Engine Oils use superior technology to protect current and older model low-emissions engines equipped with exhaust after-treatment systems and other new design features. These products exceed the API CJ-4 heavy duty requirements as well as existing API CI-4 PLUS and earlier categories.

- PERFORMANCE BENEFITS:**
- Formulated specifically for engines using Ultra Low Sulfur Diesel (ULSD)
  - Provides advanced soot control utilizing SootArrest™, soot dispersant chemistry
  - Offers advantages for current model year and older heavy duty commercial trucks and other diesel-fueled applications, including off-road equipment
  - State-of-the-art wear control technology for reduced wear
  - Exceptional oxidation and thermal protection for operating at extreme temperatures
  - Extends diesel particulate filter (DPF) life
  - SAE 10W-30 improves fuel economy and cold cranking lubrication

- PERFORMANCE CAPABILITIES:**
- Equipment requiring API CJ-4, CI-4 PLUS, CI-4, SM
  - Detroit Diesel 93K218 (SAE 15W-40 only)
  - Caterpillar ECF-3
  - Mack EO-O Premium Plus (SAE 15W-40 only)
  - Cummins CES 20081
  - Volvo VDS-4 (SAE 15W-40 only)
  - Mercedes 228.31 (SAE 15W-40 only)

*\*Some performance capabilities are applicable to specific viscosity grade(s).*

**APPLICATIONS:** Recommended for use in heavy-duty service in commercial trucks, agricultural equipment, construction equipment, stationary engines, and other diesel-fueled engine applications. Permits year-round use by offering improved low temperature startability with full lubrication at high operating temperatures.

**TYPICAL PROPERTIES:**

**CITGO CITGARD® 600 MULTI-VISCOSITY GRADE ENGINE OILS**

SAE Grade	15W-40	10W-30	20W-50
Material Code	622615001	622613001	622625001
Gravity, ASTM D 4052, °API	30.1	30.8	28.7
Density, lbs/gal	7.32	7.26	7.36
Flash Point, ASTM D 92 (COC), °F (°C)	450 (232)	431 (222)	471 (244)
Viscosity, ASTM D 445, cSt at 40°C	118	81	164
cSt at 100°C	15.6	11.8	18.4
Viscosity Index, ASTM D 2270	139	140	125
HTHS Rate Viscosity at 150°C, ASTM D 4683, cP	4.3	3.55	4.8
CCS Viscosity at -20°C, ASTM D 5293, cP	5,850	6,440	6,000 (-20°C)
MRV Pumpability at -25°C, ASTM D 4684, cP	16,100	16,950	19,700 (-20°C)
MRV Yield Stress at -25°C, ASTM D 4684	<35	<35	<35
Pour Point, ASTM D 97, °F (°C)	-22 (-30)	-33 (-36)	-6 (-21)
Color, ASTM D 1500	L3.5	L3.5	L4.0
Sulfated Ash, ASTM D 874, m%	1.0	1.0	1.2
Total Base Number, ASTM D 2896, mg KOH/g	10	10	10