



CITGO® CITGARD® 700 MFE Synthetic Blend Heavy Duty Engine Oil

OVERVIEW




- A new-generation engine oil for API FA-4 compliant engines; supports the Phase II fuel efficiency standards driving the need for even more fuel-efficient heavy duty engine oils, while delivering excellent wear protection and engine durability.
- Formulated with proprietary additive technology that protects engines running at higher operating temperatures and higher fuel injection pressures, while meeting tighter wear limits and lower emission requirements.
- Provides additional fuel economy compared to API CK-4 or API CJ-4 SAE 10W-30 engine oils.

FEATURES & BENEFITS



- Engineered for maximum fuel efficiency-- up to 4% fuel economy advantage over conventional SAE 15W-40 viscosity grade oils.
- Maintains viscosity over extended service intervals.
- Up to 100% increase in oxidation protection compared to conventional CJ-4 engine oils. Always follow OEM recommendations when extending oil drain intervals.
- Advanced wear protection for newer FA-4 compliant engines.
- Reduced air entrainment in high-pressure hydraulic fuel injection systems.

APPLICATIONS




- For use in API FA-4 compliant engines.
- Refer to equipment owner's manual for proper lubricant recommendation.

Approved for equipment requiring:
Cummins CES 20087
Detroit Diesel DFS 93K223

CITGARD® 700 MFE Synthetic Blend Heavy Duty Engine Oil vs API CK-4 or CJ-4.

	More Robust Additive System than API CJ-4 Oil	Enhanced Durability Requirements	SAE Grades	High Temperature High Shear Viscosity	Fuel Economy	Back Serviceable	Recommended by OEMs	Applications
API CK-4			0W-30 and heavier	 >3.5 cP	 Better			
API FA-4			0W-30 5W-30 10W-30	 2.9-3.2 cP	 Best			

APPLICATIONS



PROPERTIES



Typical Properties for CITGO CITGARD 700 MFE Synthetic Blend Heavy Duty Engine Oil SAE 10W-30:

SAE Grade	10W-30
Material Code	622722001
Gravity, ASTM D4052, °API at 60°F	31.5
Pounds/Gallon at 60°F	7.25
Specific Gravity at 60°F	0.87
Viscosity ASTM D445	
cSt at 40°C	66
cSt at 100°C	10.0
Viscosity Index	136
CCS Viscosity, cP, @ Temperature	5,680 @ -25°C
MRV Viscosity, cP, @ Temperature	15,500 @ -30°C
MRV Yield Stress, Pa, @ Temperature	<35
Pour Point, °F (°C)	-33 (-36)
Flash Point, COC, °F (°C)	446 (230)
Noack Evaporative, ASTM D5800, % Loss	12.7
Color, ASTM D1500	L3.5
Total Base Number, ASTM D2896	10
Sulfated Ash, ASTM D874, % wt	1.0

CITGO and CITGARD are registered trademarks of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners. Values shown are typical values only and do not constitute a specification. The information contained herein is subject to change without notice.